

AURO^N

N-Type TOPCon Mono Bifacial Dual Glass Module

605-630W ***NRBK-33***

Key Product Features



High conversion efficiency

Module efficiency increases to 23.32%



Bifacial power generation

Both sides absorb sunlight to generate power
5%-32% power generation gain



Excellent low-light performance

Better low-light power generation performance
in low radiation environment such as haze and
cloudy days



Zero LID

Excellent antidegradation capability
to achieve zero LID



SMBB Technology

16BB has better light trapping and
current collection to improve module
power output



PID Resistance

Excellent Anti-PID Performance guarantee via optimized
production technology and materials control



Low temperature coefficient

Peak power temperature coefficient $-0.278\%/^{\circ}\text{C}$
Excellent power generation performance in high
temperature environment



LOW LCOE (Levelized Cost of Energy)

Reduce the cost of BOS efficiently
Increase return on project investment

Comprehensive product certification

- IEC61215-1(ed.1)
- IEC61215-1-1(ed.1)
- IEC61215-2(ed.1)
- IEC61730-1(ed.2)
- IEC61730-2(ed.1)
- UL 61730-1 1st Edition
- UL 61730-2 1st Edition




Industry-leading Quality Assurance

15 year
Product warranty

30 year
linear power warranty

-0.40%
Annual degradation



● Please refer to the warranty letter for details



Solar Power



<https://solar.byd.com/en/>

+86-755-89888888

bydpv@byd.com

Electrical Data(STC*)

Module Type: NRBK-33	605	610	615	620	625	630
Rate Maximum Power(Pmax)(W)	605	610	615	620	625	630
Open Circuit Voltage(Voc) (V)	48.75	49.03	49.31	49.64	49.92	50.23
Short Circuit Current(Isc) (A)	15.81	15.84	15.87	15.89	15.90	15.91
Maximum Power Voltage(Vmp)(V)	40.55	40.83	41.11	41.42	41.72	42.03
Maximum Power Current (Imp) (A)	14.92	14.94	14.96	14.97	14.98	14.99
Module Efficiency (%)	22.40	22.59	22.78	22.95	23.14	23.32

*Standard Test Conditions (STC) : irradiance of 1000 W/m², spectrum AM 1.5 and cell temperature of 25°C

Electrical Data(NMOT*)

Module Type: NRBK-33	605	610	615	620	625	630
Rate Maximum Power(Pmax)(W)	457.6	461.4	465.2	469.0	472.8	476.7
Open Circuit Voltage(Voc) (V)	46.1	46.4	46.6	46.9	47.2	47.5
Short Circuit Current(Isc) (A)	12.76	12.78	12.81	12.82	12.83	12.84
Maximum Power Voltage(Vmp)(V)	37.9	38.1	38.4	38.6	38.9	39.2
Maximum Power Current (Imp) (A)	12.07	12.10	12.12	12.14	12.15	12.17

*Nominal Module Operating Temperature (NMOT):irradiance of 800 W/m², spectrum AM 1.5, ambient temperature 20°C, wind speed 1 m/s.

Operational Parameter

Operating Temperature	-40°C~-+85°C				
NMOT (Nominal Module Operating Temperature)	45±2°C				
Maximum System Voltage(V)	1500V DC				
Maximum Fuse Current Rating(A)	35A				
Fire Safety	Class C				
Power Tolerance	0~+5W				
Bifacial Factor	80±5%				
PG. 630W	5%	10%	15%	20%	25%
Rate Maximum Power(Pmax)(W)	662	693	725	756	788
Open Circuit Voltage(Voc) (V)	50.23	50.23	50.23	50.23	50.23
Short Circuit Current (Isc) (A)	16.71	17.50	18.30	19.09	19.89
Maximum Power Voltage(Vmp)(V)	42.03	42.03	42.03	42.03	42.03
Maximum Power Current (Imp) (A)	15.74	16.49	17.24	17.99	18.74


Mechanical Properties

Cell Type	N - type Mono-crystalline				
Number of Cells	132				
Dimension of Module	2382*1134*30mm				
Weight	32.3Kg±5%				
Front Glass	2.0mm semi-tempered coated glass				
Back Glass	2.0mm semi-tempered screen printed glass				
Frame	Anodized aluminum alloy				
Junction Box	IP68(3 Diodes)				
Cable Length	+320mm , -260mm(4.0mm ²); or Customized Length				
Packing Information	720 (36*20) pcs per 40'HQ				

Temperature Coefficient


Peak Power Temperature Coefficient	-0.278%/°C
Open-Circuit Voltage Temperature Coefficient	-0.239%/°C
Short-Circuit Current Temperature Coefficient	0.044%/°C

Drawing



I-V curve

Current-Voltage Curve (615W)
Cells temp.=25°C



Power-Voltage Curve (615W)
Cells temp.=25°C

